

جى بى . كيم

We formulate  
German Basic Chemical Products



## GBsuper pig. Guide recipe for Textile printing on cotton cloth USING GBsuper pig.

Color paste :

TO Dissolving GBsuper pig.:

\* e.g.Take (40 - 210 g ) Water Then add Slowly , (5 - 30 g) GBsuper pig powder

under stirring to form color solution

Then Add

Textile Stock thickening paste (955 -760 g) under stirring to the color solution,

Continue high speed stirring for 10 minutes

adjusting viscosity by water or GBsyn.Thickener GP. Check shade and then Printing on cotton, fixation 5 min at 150 deg.

\*Only for black min. 20g / Kg GBemulsphire OU

Textile Stock thickening paste guide recipe :

Water	.....
GBemulsphire OU	10 – 20g
GBsyn.Thickener GP	12 g
GBbinder ETOW	90 – 150
	g
	1000 g

طريقة الازابة :

\* يوضع اللون (+ 8 اضعاف الكمية ماء) على الماء مع التقليب ثم توضع عجينة الطباعة عليها مع التقليب لمدة 10 دقيقة (القوام يعدل باستخدام المتخن او الماء). viscosity 70-80 .  
\* التأكيد من اللون علي عينه قماش صغيره ثم الطباعة ثم تثبيت لمدة ٥ دقائق على حرارة ١٥٠ درجة مئوية . \* فقط في حالة الاسود يفضل اضافة كمية مضاعفة من الاملسفير .

Please note GBsuper pigment can be used directly on any paste while gentle stirring .



Cairo head office: 9,square 1163,El Shaheed Fouad Thabet St.,El Wozara square Sheraton Heliopolis.Cairo- Egypt

Tel: +20222683983, +201228099699 Fax : +202 2268466 E-mail: logistics@gb-chem.net , gbchem@gb-chem.net

Alex. Office :6, Talat Harab St.,Down Town Alexandria, Egypt

Tel.:+203 4819240, +201221148181 Fax:+203 4817565 E-mail: logistics@gb-chem.net , gbchemalex@gb-chem.net

www.gb-chem.net